

Firestone UNA-CLAD™ UC-3 Roofing Panel Cleaning Recommendations (cont'd)

- **RUST STAINS**

Hydrochloric acid, citric acid or muriatic acid, diluted with ten volumes of water, may assist in removing rust stains from fluoropolymer surfaces. Limit contact with finished surface to five minutes. Oxalic acid solutions or acetic acid (vinegar) may also be used. Flush all surfaces with copious amounts of water after use. Caution: Acid solutions are corrosive and toxic.